

Wall Thickness Chart for HDPE Pipes as per IS:4984:1995

Wall Thickness of Pipes for Material Grade PE 63														
Nominal Dia	Wall Thickness of Pipes for Pressure Ratings of													
DN	PN2.5		PN4		PN6		PN8		PN10		PN12.5		PN16	
	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.
20	-	-	-	-	-	-	-	-	2.3	2.8	2.8	3.3	3.4	4.0
25	-	-	-	-	-	-	2.3	2.8	2.8	3.3	3.4	4.0	4.2	4.9
32	-	-	-	-	2.3	2.8	3.0	3.5	3.6	4.2	4.4	5.1	5.4	6.2
40	-	-	2.0	2.4	2.8	3.3	3.7	4.3	4.5	5.2	5.5	6.3	6.7	7.6
50	-	-	2.4	2.9	3.5	4.1	4.6	5.3	5.6	6.4	6.8	7.7	8.4	9.5
63	2.0	2.4	3.0	3.5	4.4	5.1	5.8	6.6	7.0	7.9	8.6	9.7	10.5	11.8
75	2.3	2.8	3.6	4.2	5.3	6.1	6.9	7.8	8.4	9.5	10.2	11.5	12.5	14.0
90	2.8	3.3	4.3	5.0	6.3	7.2	8.2	9.3	10.0	11.2	12.2	13.7	15.0	16.7
110	3.4	4.0	5.3	6.1	7.7	8.7	10.0	11.2	12.3	13.8	14.9	16.6	18.4	20.5
125	3.8	4.4	6.0	6.8	8.8	9.9	11.4	12.8	13.9	15.5	16.9	18.8	20.9	23.2
140	4.3	5.0	6.7	7.6	9.8	11.0	12.8	14.3	15.6	17.4	19.0	21.1	23.4	26.0
160	4.9	5.6	7.7	8.7	11.2	12.6	14.6	16.3	17.8	19.8	21.7	24.1	26.7	29.6
180	5.5	6.3	8.6	9.7	12.6	14.1	16.4	18.3	20.0	22.2	24.4	27.1	30.0	33.2
200	6.1	7.0	9.6	10.8	14.0	15.6	18.2	20.3	22.3	24.8	27.1	30.1	33.4	37.0

Wall Thickness of Pipes for Material Grade PE 80

Nominal Dia	Wall Thickness of Pipes for Pressure Ratings of													
	DN	PN2.5		PN4		PN6		PN8		PN10		PN12.5		PN16
	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.
20	-	-	-	-	-	-	-	-	-	-	2.3	2.8	2.8	3.3
25	-	-	-	-	-	-	-	-	2.3	2.8	2.8	3.3	3.5	4.1
32	-	-	-	-	-	-	2.4	2.9	3.0	3.5	3.6	4.2	4.5	5.2
40	-	-	-	-	2.3	2.8	3.0	3.5	3.7	4.3	4.5	5.2	5.6	6.4
50	-	-	2.3	2.8	2.9	3.4	3.8	4.4	4.6	5.3	5.6	6.4	6.9	7.8
63	-	-	2.5	3.0	3.6	4.2	4.7	5.4	5.8	6.6	7.0	7.9	8.7	9.8
75	-	-	2.9	3.4	4.3	5.0	5.6	6.4	6.9	7.8	8.4	9.5	10.4	11.7
90	2.3	2.8	3.5	4.1	5.1	5.9	6.7	7.6	8.2	9.3	10.0	11.2	12.5	14.0
110	2.7	3.2	4.3	5.0	6.3	7.2	8.2	9.3	10.0	11.2	12.3	13.8	15.2	17.0
125	3.1	3.7	4.9	5.6	7.1	8.1	9.3	10.5	11.4	12.8	13.9	15.5	17.3	19.3
140	3.5	4.1	5.4	6.2	8.0	9.0	10.4	11.7	12.8	14.3	15.6	17.4	19.4	21.6
160	4.0	4.6	6.2	7.1	9.1	10.3	11.9	13.3	14.6	16.3	17.8	19.8	22.1	24.6
180	4.4	5.1	7.0	7.9	10.2	11.5	13.4	15.0	16.4	18.3	20.0	22.2	24.9	27.6
200	4.9	5.6	7.7	8.7	11.4	12.8	14.9	16.6	18.2	20.3	22.3	24.8	27.6	30.6

Wall Thickness of Pipes for Material Grade PE 100										
Nomin al Dia	Wall Thickness of Pipes for Pressure Ratings of									
	PN6		PN8		PN10		PN12.5		PN16	
DN	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.	Min.	Max.
20	-	-	-	-	-	-	-	-	2.3	2.8
25	-	-	-	-	-	-	2.3	2.8	2.9	3.4
32	-	-	-	-	2.4	2.9	2.9	3.4	3.7	4.3
40	-	-	2.4	2.9	3.0	3.5	3.7	4.3	4.6	5.3
50	2.3	2.8	3.0	3.5	3.7	4.3	4.6	5.3	5.7	6.5
63	2.9	3.4	3.8	4.4	4.7	5.4	5.7	6.5	7.1	8.1
75	3.5	4.1	4.5	5.2	5.6	6.4	6.8	7.7	8.5	9.6
90	4.1	4.8	5.4	6.2	6.7	7.6	8.2	9.3	10.2	11.5
110	5.0	5.7	6.6	7.5	8.1	9.2	10.0	11.2	12.4	13.9
125	5.7	6.5	7.5	8.5	9.2	10.4	11.3	12.7	14.1	15.8
140	6.4	7.3	8.4	9.5	10.3	11.6	12.7	14.2	15.8	17.6
160	7.3	8.3	9.6	10.8	11.8	13.2	14.5	16.2	18.1	20.2
180	8.2	9.3	10.8	12.1	13.3	14.9	16.3	18.2	20.3	22.6
200	9.1	10.3	12.0	13.4	14.8	16.5	18.1	20.2	22.6	25.1